

**PINK SUPERBLEND GRANULAR**
**MURIATE OF POTASH**

Grade Code: PGRN

**TYPICAL CHEMICAL ANALYSIS**

<i>Component/Equivalent</i>	<i>Symbol</i>	<i>Unit</i>	<i>Typical</i>	<i>Guaranteed</i>
Potassium Chloride	KCl	%	96.3	
Potassium Oxide	K <sub>2</sub> O	%	60.7	60 Minimum
Sodium Chloride	NaCl	%	2.9	
Moisture	H <sub>2</sub> O	%	0.06	
Calcium	Ca	%	0.04	
Chloride	Cl <sup>-</sup>	%	47.6	
Magnesium	Mg	%	0.03	
Potassium	K	%	50.6	
Sodium	Na	%	1.1	
Sulfate	SO <sub>4</sub>	%	0.05	
Water Insolubles		%	0.4	

**PARTICLE SIZE DISTRIBUTION (SGN 285 - 315; UI > 45)**

	<i>Tyler Mesh</i>	<i>US Mesh</i>	<i>mm Mesh</i>	<i>Typical Cumulative %</i>	<i>Typical Range %</i>
Retained on . . .	4	4	4.750	0.5	0 - 2
	5	5	4.000	10	3 - 15
	6	6	3.350	33	20 - 50
	7	7	2.800	63	40 - 75
	8	8	2.360	86	65 - 95
	9	10	2.000	95	85 - 100
	10	12	1.700	98	95 - 100
	12	14	1.400	99.3	98 - 100
	14	16	1.180	99.4	98 - 100
	16	18	1.000	99.5	98 - 100
	20	20	0.850	99.6	99 - 100
Passing through	20	20	0.850	0.4	0 - 1

**PHYSICAL PROPERTIES**

<i>Parameter</i>	<i>Unit</i>	<i>Typical/Range</i>
Bulk density	lb/cu ft	65 - 75
	kg/m <sup>3</sup>	1040 - 1201
Angle of repose	degrees	40

*Typical results are based on product expectations at load port.*

*< signifies "less than" the stated detection limit.*

*To the best of Canpotex's knowledge and belief, the information contained herein is accurate and reliable. The analysis values listed as 'Typical' in the above specifications are average values compiled from composite sample analysis and should not be considered a guaranteed specification, unless otherwise noted.*

**Revised July 2020**